

ALTIN POLİMER
YAPIŞTIRICI MALZEMELERİ SANAYİ VE TİC. LTD. ŞTİ.

TECHNICAL INFORMATION

G.101

Type of Product Aromatic poliisocyanate-prepolymer based on diphenyimethan-diisocyanate.

Typical Properties	Appearance	DIN 52002	brownish
	Viscosity 20°C	DIN 53019/1	12.000 mPAS
	Isocyanate content	DIN 53185	20 %
	Equivalent weight		430
	Density 20°C	DIN 53217/1+2	1.1 g/cm ³
	Flash Point	DIN 51758	>200 °C

Storage Gold Polimer G.101 must be protected against humidity and must be stored in unopened drums. The ideal storage temperature is 15-25 °C . Under these conditions, the material can be stored for at least 1 year.

Precautions The use of polyisocyanate-prepolymers requires special precautions. Please refer to the material safety data sheet before using. Avoid inhalation of the vapour and contact with skin and eyes. Working areas should be well ventilated with fresh air.

Use protective gloves and glasses. In case of contact with eyes, rinse immediately with plenty of water and seek medical advise. After contact with skin, immediately with plenty of water and soap. During spray application, wear suitable respiratory equipment.